

Supplier: Coace Chemical Company Limited

Manufacture Address: BLDG 4, No. 455 South Road, 2nd Ring Road, Tong'an District, Xiamen, China

Print Date: 2022/1/16



Characteristics

# **Technical Data Sheet**

Unit

**Test Method** 

#### **DESCRIPTION**

Coace<sup>®</sup> K2C is a chemical modified high density polyethylene with high content of maleic anhydride, which offers excellent adhesion to foil, paper and other polar substrates.

### **TYPICAL PHYSICAL & CHEMICAL PROPERITIES**

		• • • • • • • • • • • • • • • • • • • •	
Appearance	Granules		
Color	White or light yellow		
Density	0.93	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate (190℃2.16kg)	1-4	g/10min	ASTM D1238
Maleic Anhydride Content	High	wt%	COACE Method [1]

Notes [1] LOW < 0.4wt%; Middle(0.4wt%-0.8wt%); High≥0.8wt%.

**Value** 

#### **APPLICATIONS**

To be used as the adhesive for composite structure materials, which contain the matelplastic panels, muli-layers, etc.

To be used as compatibilizers for polyolefin compounds, and other masterbatch.

## **STORAGE, HANDLING & SAFETY**

Coace <sup>®</sup> K2C should be stored in dry conditions and protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

#### SHELF LIFE

2 years from the date of delivery, in unopened packaging.

For any other application over this limit, please contact with your COACE Chemical representative.

This fact sheet is intended as general advice.

Disclaimer: The information submitted in this publication is based on current COACE knowledge and experience. In view of the many factors that may affect its application, this data does not relieve the user from carrying out their own tests. The data does not imply assurance of certain properties or of suitability for a specific purpose. It is the responsibility of the user to ensure that any proprietary rights and existing laws and legislation are observed.