

# K2D

## Technical Data Sheet

### DESCRIPTION

Coace<sup>®</sup> K2D is a chemical modified polyethylene , which offers excellent adhesion to foil, paper and other polar substrates.

### TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Characteristics	Value	Unit	Test Method
Appearance	Granules		
Color	White or light yellow		
Density	0.92	g/cm <sup>3</sup>	ASTM D792
Melt Flow Rate ( 190℃2.16kg)	3-6	g/10min	ASTM D1238
Maleic Anhydride Content	Middle	wt%	COACE Method <sup>[1]</sup>

Notes <sup>[1]</sup> LOW <0.4wt%; Middle(0.4wt%-0.8wt%); High≥0.8wt%.

### APPLICATIONS

To be used as hot melt adhesive for aluminum foil and polyethylene composite sheet.

To be used as anti-corrosion coating of steel pipes, iron pipes, lead pipes, etc.

To be used as hot melt adhesive for steel mesh skeleton plastic composite pipe.

### STORAGE, HANDLING & SAFETY

Coace<sup>®</sup> K2D should be stored in dry conditions and protected from UV-light. Improper storage conditions may cause degradation and have consequences on physical properties of the product.

### SHELF LIFE

2 years from the date of delivery, in unopened packaging.

For any other application over this limit, please contact with your COACE Chemical representative.

This fact sheet is intended as general advice.

Disclaimer: The information submitted in this publication is based on current COACE knowledge and experience. In view of the many factors that may affect its application, this data does not relieve the user from carrying out their own tests. The data does not imply assurance of certain properties or of suitability for a specific purpose. It is the responsibility of the user to ensure that any proprietary rights and existing laws and legislation are observed.